

Technical Analyse of BITUMEN 60/70

| Specification | Test Result | Method |
|---|-------------|---------------|
| Specific gravity At 25 DFG C | 1 – 1.06 | D-70 |
| Penetration At 25 DFG C | 60/70 | D-5 |
| Softening Point (DFG C) | 49/56 | D-36 |
| Ductility At 25 DFG C(cms) | > 100 | D-113 |
| Loss of heating (PCT WT) | < 0.2 | D-6 |
| Drop in Penetration after heating (PCT) | < %20 | D-6 & D-5 |
| Flash point (DFG C) | > 250 | D-92 |
| Solubility in CS ₂ (PCT WT) | > 99.5 | D-4 |
| Spot test | Negative | A.S.H.O.T 102 |
| Wax content | < 2.0 | |

Please visit this product on:

[Bitumen 60/70](#)

Website: <http://www.blackgold.ae>