

Technical Analyse of

OGILSONITE (Natural Asphalt)

No	Properties	Value
1	Ash content (Wt %)	A: Below 5 % B: Below %10 C: 10 - 15% D: 15 - 20% E: 20 - 30%
2	Moisture content (Wt %)	3-5%
3	Volatile mater (Wt %)	60_65
4	Fixd carbon (Wt %)	25_35
5	Solubility in cs2 (Wt %)	85_90
6	Solubility in tce (Wt %)	60_70
7	Normal heptan in sol (Wt %)	60_70
8	specific Gravity (25%)	1.1_1.2
9	Colour	Black
10	Softening point	190_230
11	Pentration (25 c)	0_2
12	carbon (Wt %)	75_82
13	Hydrogen (Wt %)	6_9
14	Nitrogen (Wt %)	0.8_1.5
15	Sulphur (Wt %)	3_6
16	Oxygen (Wt %)	1.5_2.5

Please visit this product on:

[Gilsonite](#)

Website: <http://www.blackgold.ae>