

Technical Analyse of

OXIDIZED BITUMEN 115/15

Specification	Test Result	Method
Specific gravity At 25 DFG C	1.06 approx.	D-70
Penetration At 25 DFG C	10/20	D-5
Softening Point (DFG C)	110/120	D-36
Ductility At 25 DFG C(cms)	1.5 min	D-113
Loss of heating (PCT WT)	0.2 max	D-6
Flash point (DFG C)	260 min	D-92
Solubility in CS ₂ (PCT WT)	99 min	D-4

Please visit this product on:

[Oxidized Bitumen 115/15](#)

Website: <http://www.blackgold.ae>