

Technical Analyse of

BITUMEN VISCOSITY GRADE VG-40

No	Properties	RANGE
1	ABSOLUTE VISCOSITY °60C POISE MIN	3200
2	KINEYATIC VISCOSITY °135C CST MIN	400
3	FLASH POINT MIN°C	220
4	SOFTENING POINT MIN °C	50
5	PENETRATION 0.1 MIN. 25 °C	40-60
6	DVCTILITY ON MIN .°25C	25
7	VICOSITY RATIO °60C MAX	4
8	SOLURILITY IN TCE MIN	99

Please visit this product on:

[Bitumen Viscosity Grade](#)

Website: <http://www.blackgold.ae>